

**ADVAMET[®] Feedstock for Metal Injection Molding (MIM)
TYPICAL CERTIFICATION**

P/N: 17-4PH-S7

Product: Prealloyed 17-4 PH SS
Nominal Metal Composition: Water Atomized 17-4PH SS (Rounded)
Nominal Binder Content: 7.0%

Binder: Proprietary wax-polymer base binder
Metal Powders: 9 - 11 μ Rounded water atomized 17-4PH SS

Chemical Composition (Weight %)

Cr	15.5 – 17.5	Si	1.00 max	C	0.07 max
Ni	3.0 – 5.0	Mn	1.00 max	N	Report
Cu	3.0 – 5.0	P	0.04 max	O	Report
Cb, Ta	0.15 – 0.45	S	0.03 max	Fe	Balance

Viscosity

12,500 \pm 6,250 Poise at 175 C per ASTM D1238 modified
(Process details available on request)

Density

4.95 \pm 0.05 g/cm³ (measured with helium pycnometer)

Notes

1. Composition of metal constituents is determined by calculation from vendor data.
2. Composition of sintered material, particularly for C and O contents, depends on processing used by customer.
3. Properly processed feedstock will conform to MPIF Standard 35 Specification MIM-17-4PH.

Supplier

Advanced Metalworking Practices, LLC
401 Industrial Dr., Carmel, IN 46032 USA
Phone: 317-843-1499 Fax: 317-843-9359
Web Site: www.advancedmetalworking.com
August 19, 2010